



POLYZOL TEX (FT426)

Main Characteristics

Number of components

One pot/ Turquoise colour

Solid content (unsensitized) %

35 %

Preparing the Screen

- New screen should be abraded with Screenprep (SPR034) before use for optimum stencil durability.
- Degreasing the screen use Degreaser Plus (P-6419)

Coating

Manual

- Apply one or two coats of Polyzol Tex, wet on wet, to the print side of screen.
- Apply one or two coats this emulsion, wet on wet, to the squeegee side of screen.
- If a higher build of Polyzol Tex is required extra coats should be applied, wet on wet to the squeegee side.

Automatic

- When using on automatic coating machine, a simultaneous single coat on each side of the screen is recommended.
- If higher builds are required, extra coats should be applied to the squeegee side of the screen.

Drying

Put coated screen in hot air oven with squeegee side up. Do not exceed 40 °C.

Table of Exposure Guide

Light Source	Distance	Length of Exposure Time*
125W HPR Mercury Vapour Lamp	50 cm.	360-420 Seconds
50 Amp Open Carbon Arc	120 cm.	650-780 Seconds
1000W Metal Halide	120 cm.	360-420 Seconds
2000W Metal Halide	120 cm.	180-210 Seconds
3000W Metal Halide	120 cm.	115-145 Seconds
5000W Metal Halide	120 cm.	70-90 Seconds
6000W Metal Halide	120 cm.	55-75 Seconds

* Using 48-70W Screen Mesh with both sides coated twice with sensitized emulsion.

Developing

Place the screen in washout booth and gently spray both sides, increase the spray pressure slightly. Continue developing until or parts of the image appear clean and sharp.

Spotting

Check for pinholes or blemishes. Spot out with a suitable filler use Screen Filler (22997)

Reclaiming the Screen

- Screenstrip Powder (SST002) thoroughly to both side of the stencil.
- Screenstrip Liquid (SST004) thoroughly to both side of the stencil.

Recommended inks

Water based ink and plastisol ink.

Caution

Special safelight is not essential, but yellow or weak illumination is desirable.

Features

- One pot Photopolymer emulsion.
- Excellent latitude, resolution and definition.
- Fast exposure.
- Long print durability.
- For the textile industry.

Standard Packing

5 Kg and 1 Kg

Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Polyzol Tex* in Chaiyaboon Material Safety Data Sheet.

Storage

- FT426 should be stored in as cool a temperature as possible not below 0°C or over 35 °C
- FT426 be stored for 15 months.
- Screen coated in advance will last stored at 20°C and in complete darkness.
- With longer storage of pre-coated screen, the emulsion can absorb moisture from the environment. It is therefore advisable to dry again prior to exposing.

FT426 2-1101