



## TEXTO INK (TO)

### Main Characteristics

#### Ink Type

One Pack – Water Based

#### Drying

- Jet dry : 3-5 minutes
- Air dry : 24 hours
- Final step oven : 140-150 °C 1-3 minutes

#### Thinning

- 5-10% Water

#### Cleaning

- Water
- For heavy ink stains, Screensolve (SSO038) can be used.

#### Mesh

- P36-90 to P77-55 Monofilament

#### Stencil Type

- All water-resistant direct Emulsion photo-stencils

#### Recommended

- T326 Diazol Tex
- FT426 Polyzol Tex

#### Application

Light shade fabrics made wholly or partly of natural fibres such as cotton

#### Important

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

#### Colours Range

23 Colours : 14 Standard, 5 Fluorescent and 4 Trichromatic colours

### Features

- Suitable for light shade fabrics made wholly or partly of natural fibres such as cotton.
- Long lasting colour brightness.
- Excellent wash resistance.

### Available Colours

#### Standard Colours

TO100 Black

TO400 Light Orange

TO624 Royal Blue

TO791 Light Brown

TO200 White

TO520 Scarlet

TO645 Navy Blue

TO861 Gold

TO330 Light Chrome

TO590 CMS Violet

TO720 Brilliant Green

TO090 Clear

TO340 Mid Chrome

TO623 Mid Blue

TO721 Bright Green

#### Fluorescent Colours

TO381 Fluorescent Yellow

TO581 Fluorescent Red

TO582 Fluorescent Pink

TO781 Fluorescent Green

TO482 Fluorescent Orange

#### Trichromatic Colours

TO110 Trichromatic Black

TO310 Trichromatic Yellow

TO510 Trichromatic Magenta

TO610 Trichromatic Cyan

**Standard Packing**

50 Kg, 25 Kg, 3.5 Kg, 1 Kg and 500 g containers.

**Safety and Handling**

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- TO ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of TO ink** in Chaiyaboon Material Safety Data Sheet, available on request.

**Storage**

- TO ink should be stored in a sealed container between 5-25 °C.
- Store in a well ventilated place.

