



DIAZOL XTRA (G225)

Main Characteristics

Type

Two Pack/Violet colour

Sensitizer Type

Powder

Solid content (unsensitized) %

40 %

Instruction for use

- Cut or tear the powder diazo sachet.
- Add the powder sensitizer to the bottle and add water until the bottle is approximately 2/3 full.
- Shake the bottle well until the contents have dissolved.
- Add sensitizer solution emulsion and stir well before use.
- Leave the emulsion to de-gas for 1 hrs before use.

Preparing the Screen

- New screen should be abraded with Screenprep (SPR034) before use for optimum stencil durability.
- Degreasing the screen use Degreaser Plus (P-6419)

Coating

Manual

- Apply one or two coats of Diazol Xtra, wet on wet, to the print side of screen.
- Apply one or two coats of this emulsion, wet on wet, to the squeegee side of screen.
- If a higher build of Diazol Xtra is required extra coats should be applied, wet on wet to the squeegee side.

Automatic

- When using on automatic coating machine, a simultaneous single coat on each side of the screen is recommended.
- If higher builds are required, extra coats should be applied to the squeegee side of the screen.

Drying

Put coated screen in hot air oven with squeegee side up. Do not exceed 40 °C.

Table of Exposure Guide

Light Source	Distance	Length of Exposure Time*
125W HPR Mercury Vapour Lamp	50 cm.	630-730 Seconds
50 Amp Open Carbon Arc	120 cm.	1080-1200 Seconds
1000W Metal Halide	120 cm.	630-730 Seconds
2000W Metal Halide	120 cm.	310-370 Seconds
3000W Metal Halide	120 cm.	210-250 Seconds
5000W Metal Halide	120 cm.	120-160 Seconds
6000W Metal Halide	120 cm.	90-130 Seconds

* Using 120-34Y Screen Mesh with both sides coated twice with sensitized emulsion.

Developing

Place the screen in washout booth and gently spray both sides, increase the spray pressure slightly. Continue developing until or parts of the image appear clean and sharp.

Spotting

Check for pinholes or blemishes. Spot out with a suitable filler use Screen Filler (22997)

Reclaiming the Screen

- Screenstrip Powder (SST002) thoroughly to both side of the stencil.
- Screenstrip Liquid (SST004) thoroughly to both side of the stencil.

Recommended inks

Solvent based ink and UV based ink.

Caution

Special safelight is not essential, but yellow or weak illumination is desirable.

Features

- Diazo sensitized emulsion.
- Highly resistant to strong solvents.
- Very easy to reclaim.
- The tack free surface of the emulsion makes it ideal for printing on to PVC.
- For high quality graphic printing.

Standard Packing

Emulsion : 1 Kg use with sensitizer code A7.5 (7.5 g)
 : 5 Kg use with sensitizer code B37.5 (37.5 g)

Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Diazol Xtra* in Chaiyaboon Material Safety Data Sheet.

Storage

- G225 should be stored in as cool a temperature as possible not below 0 °C or over 35 °C.
- Unsensitizer G225 be stores for 36 months.
- Diazo sensitizer should be stored for 12 months.
- Screen coated in advance will last stored at 20 °C and in complete darkness.
- With longer stored of pre-coated screen, the emulsion can absorb moisture from the environment. It is therefore advisable to dry again prior to exposing.

G225 2-1102

The information and recommendations contained in this Product information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product information sheet out of date and users are requested to ensure that they follow current recommendations.