



SCREENFIX (SFX001)

Main Characteristics

Product Characteristics

Viscous/Red colour

Instruction for use

- Mix the Screenfix and Catalyst in a ration of 10:1 by weight.
- Ensure the two parts are mixed in the correct ratio, as lack of or excessive catalyst can lead to poor solvent resistance.
- Ensure that the components are mixed in a clean container.
- Keep the container tightly closed after use to prevent reaction with moisture from the air.
- Do not mix more adhesive than is likely to be used within the 30 min. (approx.) pot-life.
- Keep Screenfix at the normal room temperature. Avoid keeping Screenfix at a temperature lower than 0°C (32°F), as this will cause the product to thicken. Screenfix can be brought back to its normal consistency by bringing it back to room temperature (20°C)

Important

- Shake the Screenfix and Catalyst before use.

Features

- 2 component frame adhesive.
- Applicable to metal and wooden frame.
- Easy to use.
- Smooth finish.
- Fast dry.

Standard Packing

Screenfix : 5 ltr. and 1 ltr.

Catalyst : 100 ml.

Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- SFX001 should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Screenfix* in Chaiyaboon Material Safety Data Sheet.

Storage

- Screenfix should be stored in a cool dry place at a temperature lower than 0 °C.
- Away from direct sunlight.
- Containers should be tightly closed immediately after use, to prevent solvent evaporation and reaction with moisture from the air.
- SFX001 can be stored for 24 months.



CHAIYABOON
— inKnovation —