



POLYZOL PLUS S (FG226)

Main Characteristics

Type

One pot/Blue colour

Solid content (unsensitized) %

38 %

Preparing the Screen

- New screen should be abraded with Screenprep SPR034 before use for optimum stencil durability.
- Degreasing the screen, use Degreaser Plus P-6419

Coating

Manual

- Apply one or two coats of Polyzol Plus S, wet on wet, to the print side of screen.
- Apply one or two coats of this emulsion, wet on wet, to the squeegee side of screen.
- If a higher build of Polyzol Plus S is required extra coats should be applied, wet on wet to the squeegee side.

Automatic

- When using an automatic coating machine, a simultaneous single coat on each side of the screen is recommended.
- If higher builds are required, extra coats should be applied to the squeegee side of the screen.

Drying

Put coated screen in hot air oven with squeegee side up. Do not exceed 40 °C.

Table of Exposure Guide

Light Source	Distance	Length of Exposure Time*
3000W Metal Halide	100 cm.	30-40 Seconds

* Use 120-34Y Polyester Screen Mesh.

Developing

Place the screen in washout booth and gently spray both sides , increase the spray pressure slightly. Continue developing until or parts of the image appear clean and sharp.

Spotting

Check for pinholes or blemishes. Spot out with a suitable filler use Screen Filler 22997

Reclaiming the Screen

- Screenstrip Powder SST002 thoroughly to both side of the stencil.
- Screenstrip Liquid SST004 thoroughly to both side of the stencil.

Recommended inks

- Solvent based ink and UV based ink.

Caution

Special safelight is not essential, but yellow or weak illumination is desirable.

CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
 Tel : +662-533-2533, +662-994-5199
 Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com
 e-mail : sale_cb@cbg.in.th



Features

- One pot photopolymer emulsion.
- Excellent latitude, resolution and definition.
- Fast exposure.
- Long print durability.
- For PCB and high quality graphic printing.

Standard Packing

Emulsion : 5 Kg and 1 Kg

Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Polyazol Plus S* in Safety Data Sheet.

Storage

- Storage temperature should not be over 25 °C. It should be stored in a dry location with good ventilation and away from heat or ignition sources.
- When stored under these conditions, It is expected to have a shelf-life of 12 months. from the date of manufacture.
- Close the bottle tightly after every use.

Certified Standards

- FG226 is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

FG226 2-2101