



# DIAZOL TEX (T326)

## Main Characteristics

### Number of components

Two Pack/Blue colour

### Sensitizer Type

Powder

### Solid content (unsensitized) %

38 %

### Instruction for use

- Cut or tear the powder daizo sachet.
- Add the powder sensitizer to the bottle and add water until the bottle is approximately 2/3 full.
- Shake the bottle well until the contents have dissolved.
- Add sensitizer solution emulsion and stir well before use.
- Leave the emulsion to de-gas for 1 hr before use.

### Preparing the Screen

- New screen should be abraded with Screenprep (SPR034) before use for optimum stencil durability.
- Degreasing the screen, use Degreaser Plus (P-6419)

### Coating

#### Manual

- Apply one or two coats of Diazol Tex, wet on wet, to the print side of screen.
- Apply one or two coats of this emulsion, wet on wet, to the squeegee side of screen.
- If a higher build of Diazol Tex is required extra coats should be applied, wet on wet to the squeegee side.

#### Automatic

- When using an automatic coating machine, a simultaneous single coat on each side of the screen is recommended.
- If higher builds are required, extra coats should be applied to the squeegee side of the screen.

### Drying

Put coated screen in hot air oven with squeegee side up. Do not exceed 40 °C.

### Table of Exposure Guide

Light Source	Distance	Length of Exposure Time*
3000W Metal Halide	100 cm.	35-45 Seconds

\* Using 48-34W Polyester Screen Mesh.

### Developing

Place the screen in washout booth and gently spray both sides, increase the spray pressure slightly. Continue developing until or parts of the image appear clean and sharp.

### Spotting

Check for pinholes or blemishes. Spot out with a suitable filler with emulsion dried and re-exposed.

### Reclaiming the Screen

- Screenstrip Powder (SST002) thoroughly to both side of the stencil.
- Screenstrip Liquid (SST004) thoroughly to both side of the stencil.

### Recommended inks

Water based ink and Plastisol ink.

### Caution

Special safelight is not essential, but yellow or weak illumination is desirable.

## CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand  
Tel : +662-533-2533, +662-994-5199  
Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com  
e-mail : sale\_cb@cbg.in.th



### Features

- Diazo sensitized emulsion.
- Excellent edge definition and mesh bridging.
- Long print durability.
- For textile printing.

### Standard Packing

Emulsion : 1 Kg use with sensitizer code A5  
          : 5 Kg use with sensitizer code B25

### Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Diazol Tex* in Safety Data Sheet.

### Storage

- Emulsion and sensitizer should be stored in temperature not over 25 °C.
- Unsensitized emulsion should be stored under similar conditions and can be stored for 24 months.
- Diazo sensitizer should be stored under similar conditions and can be stored for 12 months.
- Close the bottle tightly after every use.

### Certified Standards

- T326 is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

T326 2-2101