



PP BATTERY CASE INK (PPB)

Main Characteristics

Finish

Gloss

Ink Type

One Pack / Solvent-Based

Drying

- Air dry : 15-20 minutes
- Jet dry : 70 °C 1-2 minutes

Thinning

- 10-15 % Retarder 6032

Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

Mesh

- P90-48 to P120-34 Monofilament
- N90-44 to N120-35 Monofilament

Stencil Type

- All solvent resistant direct Emulsion photo-stencils

Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

Coverage & Mesh No.

- 55-65 m²/Kg (Polyester Mesh No. P120-34 or Nylon Mesh No. P120-35)

Application

- Untreated Polypropylene (PP) and Treated Polypropylene (PP)

Caution

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

Colours Range

9 Colours : 2 Standard and 7 CMS colours

Features

- Untreated Polypropylene (PP) and Treated Polypropylene (PP).
- Very good abrasion resistance.
- Excellent adhesion and durability.

Available Colours

Standard Colours

PPB100 Black

PPB200 White

PPB090 Clear

CMS Base Colours

PPB327 Yellow GS

PPB507 Red YS

PPB560 Magenta

PPB700 Green

PPB347 Yellow RS

PPB550 Red BS


PPB600 Blue

CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
Tel : +662-533-2533, +662-994-5199
Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com
e-mail : sale_cb@cbg.in.th



Standard Packing

1 Kg container.

Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- PPB ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of PPB ink** in Safety Data Sheet, available on request.

Storage

- Storage temperature should not be over 40 °C. It should be stored in a dry location with good ventilation and away from heat or ignition sources.
- When stored under these conditions, It is expected to have a shelf-life of 24 months from the date of manufacture.
- Close the bottle tightly after every use.

Certified Standards

- PPB ink is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

