



# RUBBER EVA INK (SVA)

## Main Characteristics

**Finish**

Semi Gloss

**Ink Type**

One Pack / Solvent-Based

**Drying**

- Air dry : 10-15 minutes
- Oven stoving : 40-60 °C 2-3 seconds

**Thinning**

- 10-15 % Retarder 6032
- 10-15 % Fast Retarder 2999

**Cleaning**

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

**Mesh**

- P36-90 to P90-48 Monofilament

**Stencil Type**

- All solvent resistant Emulsion

**Recommended**

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

**Coverage & Mesh No.**

- 23-43 m<sup>2</sup>/Kg (Polyester Mesh No. P90-48)

**Application**

- All EVA Substrate

**Important**

- Stir well before use.
- Full test adhesion should be made prior to printing.

**Colours Range**

11 Colours : 2 Standard and 9 CMS colours

## Features

- Suitable for all EVA Substrate.
- Excellent adhesion and flexibility.
- Fast dry.

## Available Colours

**Standard Colours**

SVA100 Black

SVA200 White

SVA090 Extender Base For SVA Ink

SVA093 Primer For SVA Ink

**CMS Based Colours**

SVA327 Yellow GS

SVA500 Red YS

SVA560 Magenta

SVA600 Blue

SVA347 Yellow RS

SVA550 Red BS

SVA590 Violet

SVA700 Green

SVA407 Orange

**CHAIYABOON BROTHERS CO., LTD.**

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand  
Tel : +662-533-2533, +662-994-5199  
Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com  
e-mail : sale\_cb@cbg.in.th



### Standard Packing

25 Kg, 5 Kg and 1 Kg container.

### Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- SVA ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of SVA ink** in Safety Data Sheet, available on request.

### Storage

- Storage temperature should not be over 40 °C. It should be stored in a dry location with good ventilation and away from heat or ignition sources.
- When stored under these conditions, It is expected to have a shelf-life of 24 months from the date of manufacture.
- Close the bottle tightly after every use.

### Certified Standards

- SVA ink is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

