



PAPER AND BOARD FLUORESCENT INK (PABF)

Main Characteristics

Finish

Satin

Ink Type

One Pack / Solvent-Based

Drying

- Jet dry : 70 °C 10-15 seconds
- Jet dry : 80-100 °C 10-15 minutes (Coated Metal)
- Air dry : Not over 15 minutes

Thinning

- 20 % Thinner 2900
- Hot shop condition 20 % Retarder 6032

Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be use

Mesh

- P90-48 to P120-34 Monofilament

Stencil Type

- All solvent-resistant direct Emulsion photo-stencils

Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

Coverage & Mesh No.

- 35-45 m²/Kg (Polyester Mesh No. P90-48)

Application

- Paper and PS

Important

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

Colours Range

5 Colours : 6 Fluorescent colours

Features

- Printing onto Paper and Polystyrene/PS.
- Excellent screen stability and suitable for manual and automatic printing.
- Fast drying and satin finish.

Available Colours

Fluorescent Colours

PABF381 Yellow

PABF581 Red

PABF681 Blue

PABF781 Green

PABF482 Orange

PABF582 Pink

Standard Packing

25 Kg, 5 Kg and 1 Kg container.


CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
Tel : +662-533-2533, +662-994-5199
Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com

e-mail : sale_cb@cbg.in.th



Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- PABF ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of PABF ink** in Safety Data Sheet, available on request.

Storage

- Storage temperature should not be over 40 °C. It should be stored in a dry location with good ventilation and away from heat or ignition sources.
- When stored under these conditions, It is expected to have a shelf-life of 24 months from the date of manufacture.
- Close the bottle tightly after every use.

Certified Standards

- PABF ink is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

